

TEST REPORT



Korea Institute of Footwear & Leather Technology Address : 152, DangGamSeo-Ro, BusanJin-Ku, Busan, Korea Tel.:(051)897-9701 ~4,FAX:(051) 897-9766	Certificate No.: T-23-0663 Page(1)/(1)Pages	
---	--	---

1. Client
 - Name : MEC INDUSTRIES
 - Address : 30-40, DONGNAM-RO, 8GIL, SONGPA-GU, SUEOUL, KOREA
2. Reception Date: APR . 6 , 2023
3. Completion Date: APR . 19 , 2023
4. Use of Report : QUALITY CONTROL
5. Test Sample : CLEANROOM SOCKS
6. Test Results :

TEST ITEM	UNIT	R E S U L T S	TEST METHOD
Hydrolysis test (Appearance change)	-	No damage	Autoclave (121±1)℃, Steam, 10 h
		No damage	Autoclave (121±1)℃, Steam, 15 h
		No damage	Autoclave (121±1)℃, Steam, 20 h
		No damage	Autoclave (121±1)℃, Steam, 25 h

※Appearance change check : Melting, Hole
Appendix 1 Page

Korea Institute of Footwear & Leather Technology




F-P-20-04(0)

KIFLT

A4[210×297mm]

비고: 우리연구원은 국제 공인시험기관(KT-426)입니다. 본 성적서는 신청자가 의뢰 시 제공한 시료 및 시료명에 대한 결과이며, 제품의 품질을 보증하지는 않습니다. 본 성적서는 우리연구원의 사전 동의 없이 상업적 이익을 목적으로 하는 선전·광고 및 법적자료로 사용될 수 없습니다.

본 성적서는 www.easycerti.co.kr에서 진위확인이 가능합니다(발급후 4년) / The authenticity can be confirmed at www.easycerti.co.kr(within 4 years after issuance)



Appendix) T-23-0663

KIFLT

- Specimen (10 h) -



- Specimen (15 h) -



- Specimen (20 h) -



- Specimen (25 h) -

